



Brunswick Cellulose
Brunswick, Georgia



Leaf River Cellulose
New Augusta, Mississippi

GP Cellulose, LLC
133 Peachtree Street NE
Atlanta, Georgia 30303
Phone: 404 652 6493
Quality: 912-280-6839



Technical Data Sheet

Golden Isles Pulp *Grade 4885 HD*

Pulping Process	Kraft
Bleaching Process	ECF
Wood Species	Southern Pine

Typical Properties

Average Fiber Length	
FQA Length Weighted (mm)	2.4
Kajaani Length Weighted (mm)	2.7
Basis Weight (g/m ²)	765
Caliper (mm)	0.98
Density (g/cc)	0.70
Moisture (%)	9.0
Extractives (%)	0.03
Brightness (ISO)	87.0
Specific Absorption (sec/g)	< 0.75
Specific Capacity (g/g)	9.5

Packaging

Roll Width (cm)	25 – 152
Roll Diameter (cm)	115 – 152
Core Diameter (cm)	7.6

Applications: Specialty grade Golden Isles 4885 Hi-Density Pulp.